

PSC 250T/BASIC B

Technical Data Sheet

Power Smart Coat 250 Temperation/BASIC B

Primer material designed for heat insulation and protection of surfaces.

DOCUMENT

PSC-TDS-BASIC-B EN

VERSION

1.0

ISSUE

October 2026

Issued by

PScoat Zurynski, Oezdogan & Co GmbH
Schützenstraße 81a
58239 Schwerte · Germany
www.pscoat.international



PSC 250T/BASIC B

Power Smart Coat 250 Temperation/BASIC B

| *Primer material designed for heat insulation and protection of surfaces.*

Applying PSC 250T/BASIC B provides benefits such as:

- Convenient usage, allowing for both manual application using brush and mechanical spraying. This solution enables insulating of complex elements, such as: detailed designer elevation, technical installation etc.
- Can be diluted using water, the coating is environmental friendly.
- It is universal in application, allowing for usage on many surfaces.

APPLICATION

PSC 250T/BASIC B is designed to be used as primer for the main layer of PSC 250T. The material provides an excellent protection from corrosion, water condensation and C4/C5 chemical environment.

TECHNICAL DATA

Classification according to PN-EN 15824: 2010

No.	Parameter	Method of Examination	Declared Value
1	Water vapor penetration: – Vapor penetration factor V [g/m ² d]	PN-EN ISO 7783:2011	20±0,5
2	Water absorption [m ² ·h ^{0,5}]	PN-EN 1062-3:2008	0,01±0,2
3	Adhesion to surface [MPa]	PN-EN 1542-3:2000	≥1,0
4	Thermal durability [MPa] – after 20 cycles of freezing and refreezing	PN-EN 13687-3:2002	2,0±0,8
5	Adhesion [MPa] – to metal – to concrete	PN-EN 1542-3:2000	≥0,8 ≥1,0

Supplementary parameters

No.	Parameters	Method of Examination	Declared Value
1	SBI examination for fire reaction	PN-EN ISO 13832:2010	B-s1, d 0
2	Classification due to fire reaction: – flame range above 150 mm above flame application point during 60 s – appearing of flaming droplets/solid wastes causing the ignition of filtering paper.	PN-EN 13501-1+A1:2010 – $F_s \leq 150$ mm during 60 s – lack of flaming droplets/solid wastes causing the ignition of filtering paper.	– match – match
3	Ratio of heat conduction [W/mK]	PN-EN 1745:2004; PN-EN 1745:2004/Apl:2006	0,0324
4	Density volume [g/cm ³]		Approximately 0,8
5	Efficiency [kg/m ²] with coating thickness of 1 mm		Approximately 0,15
6	pH		8-9

SURFACE PREPARATION

PSC can be applied directly to surfaces, as long as they are in a solid condition. All surfaces must be cleared of dust, dirt, oil and loose particles. This will prevent the coating from detaching along with loose elements. The prepared surface must be dry (no water condensation) and any grease needs to be removed using a suitable formula. In case of smooth surfaces, it is recommended to matt them mechanically. After completing this procedure, the surface must be cleared of any dust, cleaned and left to dry. In order to level gravelly surfaces and remove loose particles, it is recommended to use pressure cleaners.

PREPARATION OF THE PRIMER BEFORE APPLICATION

Before using the product, it is necessary to consult the manual. The primer can be diluted with water (dilute only the amount of paint, needed for immediate coating). Amount of used water vary, depending on the temperature of the surface and environment.

During a prolonged storing, the coating can delaminate, but it is a natural process. In order to be restored to its prime condition, the coating needs to be stirred using a mixer, until it regains a consistent density.

The estimated mixing time is about 1-5 minutes while using a mechanical mixer, or 5-7 minutes if done manually. During the work session, the material needs to be mixed once per every 10 minutes.

APPLICATION OF THE COATING

It is advised to apply the coating using brush or painting aggregate, each layer not exceeding 0,1 mm. While using aggregate, it is best to follow the producer's guidelines. On smaller or narrow spots, it is advised to use a long-bristle brush, while large areas are best painted using aggregate. Not all devices are compatible with the PSC coating. We recommend using devices manufactured by the GRACO company, since they fulfill all necessary requirements. It is suggested to avoid working with the coating during rainy weather. After completing a work session, all tools need to be washed with water. The estimated drying time of one 0,1 mm layer ranges from 0,5 up to 24 hours, depending on temperature and air humidity. The next layer can be applied only after the last painted one becomes dry. The minimal temperature for the coating to become dry is +5° C.

STORAGE

PSC 250T/BASIC B needs to be stored in a undamaged container, in temperature between +5°C and +25°C. Protected from sun exposure. Transportation can be conducted in at least +5°C temperature. Containers must be secured in order to avoid freezing and damaging of the content during transportation.

REMARKS

The described product is not classified as dangerous, information given below is only a recommendation.

Keep away from children, do not eat, drink or smoke during the work session. Wear personal protection gear, such as boiler suite, gloves and goggles. After contact with eyes, wash the irritated area with water and remove contact lenses. If the symptoms last longer, immediately contact the doctor. In case of accidental eating of the coating, immediately wash mouth and contact the doctor. In case of contact with skin, wash the irritated area thoroughly with water and soap, then apply a cosmetic cream. If there is a need for medical help, show the sheet or label to the doctor. The coating is not classified as dangerous for environment and is not flammable in liquid form.

VALIDITY DATE

12 months starting from the production date placed on the package.

LEGAL DOCUMENTS

PN-EN 15824:2010 - Requirements regarding outer and inner plasters on organic binders.

Declaration of Conformity.